



**F.V.F.**<sup>®</sup>  
International S.r.l.

## EN 10025: GRADI EQUIVALENTI!

Designation		Equivalent Former Designations in							
EN 10025: 1993 Designation		According EN 10025:1990	Germany Din 17100	France NFA 35501	UK BS4360	Spain	Italy	Austria	Japan JIS G3101/6
Steel Name	Steel Number								
S185	1.0035	Fe 310-0	St33	A33	-	A3 10-0	Fe 320	St320	-
S235JR	1.0037	Fe 360B	St37-2	E24-2	-	-	Fe 360B	-	-
S235JRG1	1.0036	Fe 360BFU	U St37-2	-	-	AE 235 B-FU	-	U St360 B	SM41A
S235JRG2	1.0038	Fe 360 BFN	R St37-2	-	40B	AE 235 B-FN	-	R St360 B	SM41B
S235JD	1.0014	Fe 360c	St37-3U	E 24-3	40C	AE 235 D	Fe 360C	St360 C	-
-	-	-	-	-	-	-	-	St360 CE	-
S235J2G3	1.0116	Fe 360 D1	St37-3N	E 24-4	40D	-	Fe 360D	St360D	-
S235J2G4	1.0117	Fe 360 D2	-	-	-	-	-	-	-
S275JR	1.0044	Fe 430B	ST 442	E 28-2	43B	AE 275 B	Fe 430 B	ST 430 B	SS400
S275JD	1.0143	Fe 430C	ST 443U	E 28-3	43C	AE 275 C	Fe430 C	St430 C	-
-	-	-	-	-	-	-	-	ST 430 CE	-
S275J2G3	1.0144	Fe 430D1	ST 430 D1	E 28-4	43D	AE 275 D	Fe 430 D	ST 430 D	-
S275J2G4	1.0145	Fe430D2	-	-	-	-	-	-	-
S355JR	1.0045	Fe 510 B	-	E 36-2	50B	AE 355B	Fe 310B	-	SS490
S355JD	1.0553	Fe 510 C	ST 52-3U	E 36-3	50C	AE 355C	Fe 310C	St510C	-
S355J2G3	1.0570	Fe 510 D1	ST 52-3N	-	50D	AE 355D	Fe 310D	St510D	-
S355J2G4	1.0577	Fe 510 D2	-	-	-	-	-	-	-
S355K2G3	1.0595	Fe 510 DD1	-	E36-4	50DD	-	-	-	-
S355K2G4	1.0596	Fe 510 DD2	-	-	50DD	-	-	-	-
E 295	1.0050	Fe 490-2	ST 50-2	A 50-2	-	A 490	Fe 480	St490	-
E355	Fe 590-2	St590-2	St60-2	A 60-2	-	A590	Fe 580	St590	-
E360	1.0070	Fe 690-2	St70-2	A 70-2	-	A690	Fe 650	St590	-